



Technical Specs

Characteristics	Standard	Declared ASTM
Water Absorption	C373	$\leq 0.5\%$
Break Strength	C648	Min. 350
Scratch Hardness	MOH's Scale	5
Chemical Resistance	C650	Unaffected
Frost Resistance	C1026	Resistant
Group	SEE FAQS	4
Deep Abrasion - Unglazed Tiles	C1243	-
PEI - Glazed Tiles***	C1027	4
Minimum Bond Strength (PSI)	C482	165
Dynamic Coefficient of Friction (DCOF)	A137.1	≥ 0.42
Shade and Texture Rating	CTDA "V"	V2
Facial Dimensions	C499	Pass
Range of Thickness	C499	Pass
Warpage	C485	Pass
Wedging	C502	Pass